



R-5775K and R-5670K
Megtron 6 PPO Blend Resin System

Test Sample .006" (2-1080 @63%RC)		Dielectric Constant (Dk)	Dissipation Factor (Df)	Test Method Used
FREQUENCY	2 GHz	3.40	0.002	IPC TM 650 2.5.5.5
	4 GHz	3.40	0.003	
	6 GHz	3.40	0.003	
	8 GHz	3.40	0.004	
	10 GHz	3.40	0.004	

Dk/Df (IPC TM-650 2.5.5.5)



Megtron 6